

Stearic Acid

WILFARIN™

PRODUCT CODE		WILFARIN™ SA-1892	WILFARIN™ SA-1865	WILFARIN™ SA-1850	WILFARIN™ SA-1843	WILFARIN™ SA-1838	WILFARIN™ SA-1810	WILFARIN™ SA-1804
PRODUCT DESCRIPTION		Stearic Acid 92 %	Stearic Acid 65 %	Stearic Acid 50 % Triple Pressed	Stearic Acid 43 % Triple Pressed	Stearic Acid 38 % Triple Pressed	Rubber Grade Stearic Acid	Rubber Grade Stearic Acid
SPECIFICATION								
Acid Value	mg KOH/g	195 - 199	202 - 209	206 - 209	205 - 211	206 - 213	195 Min	195 Min
Sap. Value	mg KOH/g	196 - 200	203 - 210	207 - 210	206 - 211	207 - 214	196 Min	196 Min
Iodine Value	g I ₂ /100g	2 Max	0.5 Max	0.5 Max	0.5 Max	1 Max	4 Max	10 Max
Titre	°C	66 - 70	58 - 63	55 - 57	54 - 57	54 - 56	52 - 57	52 Min
Color	Lov, R/Y	0.5 / 2 Max	0.2 / 1.5 Max	0.3 / 1.3 Max	0.5 / 5 Max	0.5 / 1.3 Max	0.5 / 5 Max	5 / 50 Max
Moisture	%	0.2 Max	0.1 Max	0.2 Max	-	-	-	-
Unsap Matter	%	1 Max	0.5 Max	-	-	1 Max	-	-
Composition	%							
C10		-	-	-	-	-	-	VARIABLE
C12		-	-	-	1 Max	1 Max	-	
C14		-	2 Max	2 Max	2 Max	2 Max	-	
C15		-	-	0.5 Max	-	-	-	
C16		8 Max	30 - 33	45 - 49	49 - 58	57 - 65	75 Max	
C17		-	-	0.5 Max	-	-	-	
C18		92 Min	65 - 69	50 - 54	42 - 48	35 - 40	25 Min	
C18-1		2 Max	1 Max	0.5 Max	1 Max	2 Max	-	
C18-2		1 Max	0.5 Max	-	-		-	
C18-3		-	-	-	-		-	
C20		3 Max	1 Max	1 Max	-		-	
Others		-	-	-	-	-	-	
PRODUCT FORM		Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads	Liquid / Solid / Flakes / Beads
PACKAGING		PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk	PB, BB, DR, ISO, Bulk

PB = 25kg net pp laminated paper bag BB = 800kg net jumbo bag DR = 180kg steel drum ISO = 20mt iso tank



Passover



For more details and trade inquiries please contact oleo@wilmar.com.sg